

Plastifloor® 410 (USA)
Elasticised, medium-viscous
Methacrylate resin for broadcasting coatings

Application: Plastifloor® 410 is notably suitable for the production of 2.0 – 5.0 mm broadcasting coatings, which are being broadcasted with sand of corresponding particle size.

Characteristics: Plastifloor® 410 coatings dispose of outstanding mechanical strength and a high resistance to chemicals in addition to resistance against UV-aging and saponification.

Data:

Condition	liquid
Density at 68 °F	0,0022 lb/cm ³
Flash point	+50 °F
Storage, at a dark place at < 68 °F	6 months maximum

**Formulation
coating
2-5 mm:**

This formulation is suitable for floors exposed to severe mechanical and chemical loading in dry and wet areas, e.g. electrolysis and galvanizing plants, chemical production plants, acid-proof installations, dairies and butcher's trade where non-skid floors are required.

		consumption
60.0 ppW	Plastifloor® 410/20	2.20 lb/m ²
40.0 ppW	Quartz sand 0.06- 0.2 mm	1.54 lb/m ²
2.0 ppW	Hardener 50 W (at 68°F)	

This mix is applied to well-primed surfaces. If necessary, it is possible to apply a flexible membrane layer made from PF 332/Z.

Stir up the resin well before use!

Prior to use, hardener and resin must be mixed and stirred at least 1 minute, then fillers are premixed in the power mixer for app. 2 minutes. Then the coating is applied immediately by using a smoothing trowel.

Thin layers and excess filler deteriorate the liquid quantity of the material and may cause curing defects.

Plastifloor® 410 (USA)
Elasticised, medium-viscous
Methacrylate resin for broadcasting coatings

For decorative surfaces, coloured sands (resin coated), e.g. granulation 0.7-1.2 mm may be scattered onto the coating.

We recommend to seal this surface e.g. with Plastifloor® 522 or Plastifloor® 526.

**Pot life and
hardening
time at different
temperatures:**

temperature (°F)	hardener* (% by vol.)	pot life (min)	hardening time (min)
+41	4.5	app. 40	app. 80
+50	3.5	app. 30	app. 60
+68	2.0	app. 25	app. 50
+86	1.0	app. 25	app. 45

* Quantity is calculated on total formulation.

Hint:

The coating work always has to be continued only after complete curing of the preceding layer. For jobs below 41°F the application of accelerator 101 is necessary. (query data sheet!)

Storage:

Methacrylate resins are subject to the handling regulations of highly flammable materials. Plastifloor resin has to be stored cool, at temperatures between 59 – 68°F and protected from direct sun. During storage paraffin particles can be deposited. Therefore materials have to be stirred thoroughly at temperatures of 95 °F.

Please note the advice of our safety datasheet

data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.