

## Plastifloor® 522 N (USA)

Low-viscous, slightly blue  
methacrylic resin for hard sealings

**Characterization:** Plastifloor® 522 N is a newly developed hard methacrylic resin of low viscosity that is preferably used as a sealer for Plastifloor® coatings in order to improve heavy mechanical and scratch resistance as well as maintenance. The main application areas are trowel-smoothed industrial floors made of Plastifloor® 510 and Plastifloor® 418  
Plastifloor® 522 N excels in:

- improved self-leveling qualities
- minimal yellowing
- high scratch resistance by using hardener/M
- excellent chemical resistance
- high thermal endurance
- low tendency to staining

### Data:

---

Delivery form	liquid, slightly bluish
Flow time	26-32 (68°F DIN flow cup 4mm)
Density at 68°F	DIN 53217 0.0022 lb/cm <sup>3</sup>
Flash point	DIN 51755 +50 °F
Curing time	20-30 minutes (68°F and 1% hardener)
Shelf life	dark at < 68 °F 6 months maximum

---

**Application:** Stir up well all Plastifloor® resins before application! Pour the required preparation quantity into a mixing pail and stir in hardener 50W for about 1 min by using a suitable agitator. Plastifloor® 522 N is preferably applied crosswise with short hair rollers (mohair) in a layer thickness of up to 0.4 mm max (~ 14.11 oz/ft<sup>2</sup>). Layer thickness must at least be 0.2 mm (5.22 oz/ft<sup>2</sup>) and should not exceed 0.5 mm (13.04 oz/ft<sup>2</sup>) with 2 layers – depending on the required coating structure (smooth or coarse).

**Special remarks:** After stirring in the hardener, the sealer is poured out onto the floor and immediately dispersed evenly. Sealings with Plastifloor® 522 N should not be applied onto coatings with Plastifloor® 332 as the coating's high flexibility in combination with the very hard sealer Plastifloor® 522 N might cause cracking on loading. Hardener concentrations of > 2 % may cause discolorations (yellowing). Furthermore a waiting time of about 2 hours between the coatings' curing and the application of the sealer has proven. Despite the good chemical resistance of Plastifloor® 522, one has to reckon a reduced resistance when sealing coatings based on Plastifloor® 418 or 510. With these solvents (on continuous loading), a swelling by diffusion

## Plastifloor® 522 N (USA)

Low-viscous, slightly blue  
methacrylic resin for hard sealings

may take place after some time. This process depends on the sealing's layer thickness. In these cases, we thus recommend a layer thickness of 0.5 mm minimum or better a double application of Plastifloor® 522 N. Only continue coating works after complete curing of the previous layer. It has proven that intermediate grinding of the coating before applying the sealer increases intermediate adhesion and levels any unevenness (lumps, knobs)

**Preparation**      2.113 gal    Plastifloor® 522 N  
0.0211 gal hardener powder 50 W or 0.0423 gal hardener/M

### Pot life and hardening time at different temperatures:

temperature (°F)	hardener* (% by vol.)	pot life (min)	hardening time (min)
+ 41	2.0	app. 30	app. 45
+ 50	1.5	app. 20	app. 35
+ 68	1.0	app. 10	app. 22
+ 86	1.0	app. 8	app. 18

\* Quantity is calculated on total formulation and for hardener powder 50W.

**Attention:**      At temperatures below 32 °F, the resin needs to be put into a warm environment before processing - minimum 41 °F and add up to 2% hardener maximum. Basically accelerator cannot be added to sealings – neither as thinner nor as accelerator – due to yellowing aspects.

**Storage:**      Methacrylate resins are subject to the handling regulations of highly flammable materials. Plastifloor resin has to be stored cool, at temperatures between 59 – 68° F and protected from direct sun. During storage paraffin particles can be deposited. Therefore materials have to be stirred thoroughly before processing the mixture. Please note the advice of our safety datasheet.

data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.