

Plastifloor® Additive 113

Additive for Plastifloor® coatings

Uses: Plastifloor® Additive 113 is for the combination with Plastifloor® 112. The obtained resin by mixing both is a adhesive primer for Plastifloor® coatings especially on slightly damp cementitious substrates.

Properties: By adding 5 Vol.% Additive 113, a better adhesion on slightly damp cementitious substrates is being achieved.

Characteristic data:

Condition:	liquid
Flash point:	> 482°F
Storage	dark at < 68°F: at least 6 months

standard formulation:

100,0 p.b.w.	Plastifloor® 112
5,0 p.b.w.	Additive 113
3,0 p.b.w.	Hardener powder 50 W (at 68°F)

We recommend slightly broadcasting the primer with quartz sand (size 0.7-1.2 mm).

Remarks: Further coating layers with Plastifloor must only be applied after the previous layers have completely cured.

data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.