

Plastifloor® 540 (GB)

Medium-viscous, plasticized Methacrylate base resin
for the production of cove pastes

Characteristics: Plastifloor® 540 excels in elasticity, high fillability and clear curing. Thanks to its first-rate moistening characteristics on filler materials and pigments, Plastifloor® 540 is preferably used for the production of cove paste with Aerosil® or Sylothix®.

Characteristic data:

Form of delivery	liquid, blue
Flow time	35-45 sec (20°C), DIN flow cup, 4mm
Curing	25-35 min (20°C)
Density at 20°C	DIN 51757 1.0 g/cm ³
Flashpoint	DIN 51755 +10°C
Shelf-life, dark at < 20 °C	6 months maximum
Bundle	180 kg drums 25 kg, 10 kg pails

Initiator/Hardener: Hardener powder 50 W (BPO, at 50 %), temperature-dependent

Storage conditions: Storage at ≤ 25°C. Keep away from direct sun. At temperatures below + 15°C the paraffine dissolved in the bonding agent could precipitate. Stir up well before use!

VbF: A I

GISCODE: RMA 10

Customs Number: 320 820 10

Mix Ratio: 19 l Plastifloor® 540
(Paste) 1 kg Aerosil® 200

Plastifloor® 540 (GB)

Medium-viscous, plasticized Methacrylate base resin
for the production of cove pastes

Processing of Paste: The **paste** consisting of Plastifloor® 540 and Aerosil® is being mixed with coloured quartz sand (size: 0,4 – 2,0 mm) in a mix ratio of 1:3 so as to create a thixotrope compound which does not subside (trowel test). After the preparation of a well-workable compound, add Hardener 50 W (quantity depends on the soil temperature, 1-4 vol. %, see chart) Apply cove compound with a margin trowel and subsequently smooth with an accordingly curved cove trowel. If necessary, grind the cove surface after hardening, then apply Plastifloor® 522, 526 or 528 as clear sealing. Use Plastifloor® 526 in wet areas with high demands on change in temperature.

Pot life and curing-time depending on the temperature:

Temperature [°C] **)	Hardener [Vol.- %] *)	Pot life [min.]	Curing time [min.]
+ 5	4,0	ca. 20	ca. 50
+10	3,0	ca. 15	ca. 45
+20	2,0	ca. 10	ca. 25

*) Quantity of hardener refers to Plastifloor® 540

***) Temperature indications refer to temperature of resin, soil and air.

Hints: To be applied only on primed surfaces! Good ventilation during processing ensures good curing.

Information about our products, equipment, plant and processes is based on extensive research and our considerable experience in the field of applied engineering. We provide this information, which is to the best of our knowledge accurate, orally and in writing. We assume no liability other than as agreed in the terms of the individual contracts and we reserve the right to make technical modifications in the course of our product development. The aforesaid shall not relieve the Purchaser of its obligation to verify the suitability of our products and processes for the use or application intended by the Purchaser. These limitations shall also apply to the protection of third party intellectual property rights as well as applications and processes which have not been explicitly communicated by us in writing.