

# Plastifloor® 800 PUMMA hybrid coating for parking decks/pool decks

Fast installation, jointless execution on wall, plinth or coloured separations included, fully chargeable only 2 hours after installation



## 2nd sealer

Plastifloor® 528

0.4 kg/m<sup>2</sup>

coloured

acc. to RAL

## 1st sealer

Plastifloor® 528

0.4 kg/m<sup>2</sup>

coloured

acc. to RAL

## Coating

Plastifloor® 800

1.2 kg/m<sup>2</sup>

1:1 with s/l filler

fully broadcast

with quartz sand

0.6 – 1.2 mm

## Membrane

Plastifloor® 800

1.2 kg/m<sup>2</sup>

1:1 with PET s/l filler

slightly broadcast

with quartz sand

0.6 – 1.2 mm

## Primer

Plastifloor® 112/113

0.5 kg/m<sup>2</sup>

slightly broadcast

with quartz sand

0.6 – 1.2 mm