

System recommendation

Plasticoate

Repairing, grounding, coating

Repairing, grounding, coating

of smooth and mineralized roll roofing with dried out and a weathered surface, first signs of crocodile-skin-pattern with superficial capillary cracks.

1. Clean roof surface thoroughly.
2. Repairing and strengthening of all weak points with Plasticoate Plastic Cement and strengthening rolls.
3. Put Plasticoate Primer on the surface according to the grades of desiccation (0,7 till 1,5 kg/m²).

Important: If there are first signs of crocodile-skin-pattern put so much Primer on that it fills up all deepening till it creates an even surface.

4. After the Primer is dried (depending on the temperature 3 till 10 days), coat the roof with Plasticoate Roof-Coating 1,2 kg/m²

or

with Plasticoate Roof-Coating PC 1,5 kg/m².

5. Either spread the slate-grit (2 till 3 kg/m²) into the wet coat or after a waiting time of 6 months cover it with Plasticoate Aluminum Roof-15 kg/m².