

System recommendation

Plasticoate

Repairing and Coating

Repairing and Coating

of smooth an mineralized roll roofing, a little bit weathered

1. Clean the whole surface thoroughly.
2. Strengthening with Plastic Cement and Poly Star fabric roll roofing of all weak points with roof-breakthrough etc.
3. Coating of the whole roof surface with Plasticoate Roof-Coating (1,2 kg/m²)
or
Plasticoate Roof-Coating PC (1,5 kg/m²).
4. Either
spread with slate-grit into the wet roof coat right away
or
after a waiting time of 6 months, coat with Plasticoate Aluminum Roof Coating.