

Plastifloor® 332 MMA coating system for interior park decks

Fast installation, seamless installation from wall to wall, plain or colored quartz usable, fully loadable just 2 hours after installation



2nd sealer

Plastifloor® 526

0.4 kg/m²

colored

acc. to RAL

1st sealer

Plastifloor® 526

0.4 kg/m²

colored

acc. to RAL

Coating

Plastifloor® 332

1.2 kg/m²

1:1 with s/l filler

fully broadcast

with quartz sand

0.6 – 1.2 mm

Membrane

Plastifloor® 332

1.2 kg/m²

1:1 with s/l filler

slightly broadcast

with quartz sand

0.6 – 1.2 mm

Primer

Plastifloor® 112/113

0.5 kg/m²

slightly broadcast

with quartz sand

0.6 – 1.2 mm