

Viscous, plasticized synthetic resin for membranes and elastic coatings, indoors and outdoors, appropriate for tarmac, concrete and metal substrates

Application Due to its elasticity Plastifloor® 332 is ideal for producing elastic membranes after priming with Plastifloor® 112. Plastifloor® 332 membrane can be coated with Plastifloor® 418 and also with an elastic Plastifloor® 332 covering.

Characteristics: Plastifloor® 332 coatings stay elastic and abrasion-proof even at low temperatures. Thus it can also be used in coolers and outdoors. It is characterized by an especially good levelling. The use of Plastifloor® 332 in membranes minimizes fissuring in floor coverings as mechanic loads and dynamic forces are better absorbed and transferred onto the subsurface.

Characteristic data:

Form of delivery	liquid, blue
Flow time	35-45 sec (68°F), DIN flow cup,0,23622inch
Curing	30-40 min (68°F)
Shelf-life	dark at < 68°F 6 months maximum
Bundle	180 kg drum 25 kg, 10 kg pail

To enhance the intermediate adhesion, we recommend to slightly broadcast Plastifloor® 332 membranes, e.g. with quartz sand size 15 - 25 mesh. Always broadcast Plastifloor® 332 Top coverings.

Processing Notes:

Processing: Mixture production is to be effected immediately before processing by providing the filler and by adding hardener powder 50W. Mixing time with the double agitator is about 2 min. We recommend installing Plastifloor® 332 with a minimum thickness of 3 mm. Add the filler materials when the hardener has been well mixed with the resin. (1 min.)

Processing is usually done with a notched trowel or a smoothing trowel. The self-levelling cover coat can also be

evened with a squeegee. Broadcast the fresh coating with quartz sand 15 – 25 mesh or décor quartz sand, approx. 0.074 - 0.098 lb/ft² for Membrane and 0.098 - 0.123 lb/ft² for coating.

Viscous, plasticized synthetic resin for membranes and elastic coatings, indoors and outdoors, appropriate for tarmac, concrete and metal substrates

Suggested formulation:

<i>Membrane</i>	2.113 gal	primer Plastifloor® 332
	1.585 - 2.113 gal	SL Filler
	8.12 oz	hardener 50 W (at 68°F ground temperature)
<i>Coating</i>	2.113 gal	primer Plastifloor® 332
	2.113 – 2.641 gal	SL Filler
	8.12 oz	hardener 50 W (at 68°F ground temperature)

Pot life and curing times depending on temperature:

Further coating layers with Plastifloor® must only be applied after the previous layers have completely cured.

Temperature [°F]	Hardner [Vol%]	Pot life [min]	Hardening time [min]
+41	4	ca. 20	ca. 60
+50	3,5	ca. 15	ca. 45
+68	3	ca. 10	ca. 40
+86	2,5	ca. 10	ca. 30

*) Hardener quantity calculated according to Plastifloor® 332

**) temperature refers to resin, surface and air temperature

Attention: Hardener quantities below 1 Vol. % may cause polymerisation failures!

Note: Continue coating only after complete curing of the previous layer. For works below 5°C we recommend using Plastifloor Accelerator B 101. (Request data sheet!)

Storage: The handling-regulations for highly flammable materials apply to methacrylate – resins. Plastifloor® resins are to be stored cool, protected against direct sunlight and preferably at temperatures of 59 - 68 °F. During storage paraffin – particles and filler – materials may precipitate. Thus before processing, containers have to be stirred up well. Please mind the advice on our safety data sheets.

Industrial safety: Ensure sufficient ventilation during work. On processing, pay attention to the directives in the hazardous substances ordinance and to the indications of the Federal States Committee for industrial safety and safety engineering (LASI) as well as to our safety data sheets.

Plastifloor® - 332 (USA)

PLASTI CHEMIE

Produktionsgesellschaft mbH

Viscous, plasticized synthetic resin for membranes and elastic coatings, indoors and outdoors, appropriate for tarmac, concrete and metal substrates

VbF: A I
GISCODE: RMA 10
Taxnumber: 3208 2010

Data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.

12/09/2023

3 / 3

Plasti-Chemie Produktionsgesellschaft mbH
Falgardring 1
D - 08223 Falkenstein / Germany

Telefon: +49 (0) 3745 / 74432-0
Telefax: +49 (0) 3745 / 74432-27

Email: info@plasti-chemi.de
Internet: www.plasti-chemie.de